

# ContecTile 88

## Cementitious Tile Adhesive

### *Description:*

ContecTile 88 is a tile adhesive supplied in powder form, only the addition of water and proper mixing is needed to acquire putty like mix ready to be used. ContecTile 88 is available in white and grey colors.

### *Uses:*

ContecTile 88 is a cementitious tile adhesive that forms a high bond between tiles, marble and concrete or plaster on vertical and horizontal surfaces. ContecTile 88 is suitable for natural stones, ceramic, porcelain, mosaics, and cement decorative bricks, large tiles, glass mosaic tiles, etc. on walls or floors on various substrates, especially where particularly high adhesion, elasticity and moisture resistance are required (e.g. old tile layers, floors with in-floor heating, metal surfaces, swimming pools, gypsum boards, etc.).

### *Advantages:*

- Used internally and externally.
- Resist water after it completely cured.
- Thin layer, easy to achieve evenness of tiles.
- Excellent bond strength.
- Highly recommended for bathrooms, kitchens and other wet areas.
- Suitable for fixing large format tiles.
- Can be used in totally submerged conditions.
- Economical.
- Very suitable for halls and open spaces that are exposed to constant movement and heavy duty.

### *Standards:*

ISO 13007-1 and BS EN 12004 as an improved cementitious tile adhesive (C2).

### *Application:*

Substrate should be clean, sound and free from oil, grease, rust and other impurities. Absorbent substrates must be wetted to saturated surface dry (SSD) conditions.

Mix 5 to 6 liters of water with 20 kg powder of ContecTile 88 with a slow speed drill until a homogeneous, lump free consistency is achieved.

Apply ContecTile 88 onto the substrate at about 3 mm and then overrun a gain with a notched spatula. Place tile firmly onto adhesive with a twisting motion and level by tapping as required. Always make sure that the layer of spread adhesive is fresh and has not formed a skin. Adverse atmospheric conditions such as strong winds and direct sun may extremely reduce the workability time. Pointing of joints may be executed after 6 and 24 hours for walls and floors, respectively.

Application Temperature: 5-35°C

Ready to grout: 24 hrs

Pot life: 8 hrs

Open time: >20 min

### *Packaging:*

ContecTile 88 is supplied in 20 kg bags.

### *Coverage:*

Approximate 6 m<sup>2</sup> at 3mm thickness.

### ***Special Notes:***

Do not use **ContecTile 88** on painted surfaces or on steel. The product should not be exposed to moving water, frost, strong winds, and direct sunlight during application.

### ***Shelf Life/ Storage:***

Shelf life is 12 months if stored in a dry, cool, and covered location.

### ***Safety Precautions:***

**ContecTile 88** does not fall into the hazard classification of current regulations. However, it should not be swallowed or allowed to come into contact with eyes. Suitable protective gloves and goggles should be worn.

Splashes on the skin should be removed with water. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice. If swallowed seek medical attention immediately – do not induce vomiting.

08/2022-CTC revised 02/2024