

ISOFLEX HYBRID

Hybrid, polyurethane-based, elastomeric, liquid waterproofing membrane for flat roofs

Description

ISOFLEX HYBRID is a hybrid, elastomeric, waterborne, liquid waterproofing membrane for flat roofs, based on acrylic and polyurethane resins. Has with excellent bonding to various substrates, such as concrete, wood, metal and any type of waterproofing membranes and is applicable even to irregular substrates. After curing, it forms a continuous, elastic, waterproof and vapor-permeable membrane, without seams or joints, offering:

- High elasticity.
- High resistance to weather and aging.
- High whiteness and solar reflectance.
- Improvement of building energy efficiency by decreasing the roof temperature.
- Resistance to ponding water.

Certified according to EN 1504-2 and classified as a coating for surface protection of concrete. CE marked.

Certificate No.: 2032-CPR-10.11.

Fields of application

ISOFLEX HYBRID is ideal for waterproofing flat roofs, curved roofs, etc. Constitutes a simple and safe solution for waterproofing roof details, such as corners, edges and joints between different adjacent materials, as well as isolated cracks.

Furthermore, thanks to its high solar reflectance, it can be used as cool roof paint.

Technical data

Color:	white
Density:	1.40 kg/l
Elongation at break: (EN ISO 527)	550%

Water vapor permeability: Sd = 0.59 m
(EN ISO 7783-2: Class I-permeable to water vapor, Sd < 5)

Capillary water absorption: 0.01 kg/m²·h^{0.5}
(EN ISO1062-3: W₃ low, w < 0.10 kg/m²·h^{0.5})

Adhesion strength: 2.9 N/mm²
(EN 1542, requirement for flexible systems with no traffic:0.8 N/mm²)

Artificial weathering: Pass (no blistering, cracking or flaking)
(EN 1062-11, after 2000 h)

Reaction to fire: Euroclass F
(EN 13501-1)

Minimum application temperature: +5°C

Viscosity: ≈ 30,000 mPa·s
(EN ISO 2884-2)

Drying time at +20°C: 2 h (touch dry)
(EN ISO 2811-1)

Recoat time at +20°C: 18 h (touch dry)
(EN ISO 2811-1)

Directions for use

1. Substrate preparation

The substrate must be dry, clean, free of grease, loose particles, dust, etc. Any existing cavities in concrete should be repaired in advance. The substrate is then primed with the special primer ISO-PRIMER, with a consumption of approx. 200 g/m².

ISOFLEX HYBRID

2. Application – Consumption

a) Full-surface waterproofing

As soon as the primer has dried, ISOFLEX HYBRID is applied by brush or roller in two layers, with a consumption of 0.5-0.75 kg/m²/layer, depending on the substrate. The second layer should be applied crosswise, after the first one has dried and is walkable.

In areas with severe cracks, it is recommended to locally reinforce ISOFLEX HYBRID with a 10 cm wide strip of fiberglass mesh (65 g/m²) or polyester fleece (30 g/m²) along the cracks. In that case, after the primer has dried, a layer of ISOFLEX HYBRID is applied along the cracks and, while still fresh, the 10 cm wide strip of fiberglass mesh or polyester fleece is embedded lengthwise. Then, two extra layers of ISOFLEX HYBRID are applied over the entire surface.

In case of dense, multiple cracks appearing all over the surface, it is strongly recommended to fully reinforce ISOFLEX HYBRID membrane with 100 cm wide strips of fiberglass mesh (65 g/m²) or polyester fleece (30 g/m²). These placed strips must overlap by 5-10 cm. In that case, after the primer has dried, a layer of ISOFLEX HYBRID is applied as wide as the upcoming reinforcement, and, while still fresh, a strip of fiberglass mesh or polyester fleece is embedded. The same application process is followed over the remaining surface. Subsequently, two extra layers of ISOFLEX HYBRID are applied over the entire reinforcement.
Consumption: approximately 2.0-2.5 kg/m², depending on the substrate and the type of reinforcement.

b) Local waterproofing of cracks

In this case, the substrate is primed only across the cracks to a width of 10-12 cm. After the primer has dried, a layer of ISOFLEX HYBRID is applied and, while still fresh, a 10 cm wide strip of fiberglass mesh (65 g/m²) or polyester fleece (30 g/m²) is embedded lengthwise.

Then, two extra ISOFLEX HYBRID layers are applied along the cracks, completely covering the reinforcement.

Consumption: approximately 200-250 g/m of crack length.

Tools should be cleaned with water, while ISOFLEX HYBRID is still fresh.

Packaging

ISOFLEX HYBRID is supplied in 1 kg, 4 kg, 13 kg and 25 kg containers.

Shelf life – Storage

24 months from production date if stored in original, unopened packaging at temperatures between +5°C and +35°C. Protect from direct sunlight and frost.

Volatile Organic Compounds (VOCs)

According to Directive 2004/42/CE (Annex II, table A), the maximum allowed VOC content for the product subcategory i, type WB is 140 g/l (2010) for the ready-to-use product. The ready-to-use product ISOFLEX HYBRID contains 4 g/l VOC.

ISOFLEX HYBRID



ISOMAT S.A.

17th km Thessaloniki – Ag. Athanasios
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece

17

2032-CPR-10.11C

DoP No.: ISOFLEX HYBRID/1437-02

EN 1504-2

Surface protection products
Coating

Permeability to CO₂: Sd > 50m

Water vapor permeability: Class I (permeable)

Capillary absorption: $w < 0.1 \text{ kg/m}^2 \cdot \text{h}^{0.5}$

Adhesion: $\geq 0.8 \text{ N/mm}^2$

Artificial weathering: Pass

Reaction to fire: Euroclass F

ISOMAT S.A.

BUILDING CHEMICALS AND MORTARS

MAIN OFFICES - FACTORY:

17th km Thessaloniki - Ag. Athanasios Road,
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,
Tel.: +30 2310 576 000, Fax: +30 2310 722 475

www.isomat.eu e-mail: info@isomat.eu