

ISOFLEX-PU 540

One-component, polyurethane, liquid waterproofing membrane

Description

ISOFLEX-PU 540 is a one-component polyurethane liquid waterproofing membrane.

- Based on pure elastomeric, hydrophobic polyurethane resins, it offers high mechanical and chemical properties to the product.
- Forms a continuous, elastic, waterproof and vapor-permeable membrane, with no seams or joints.
- Has excellent bonding to various substrates, such as concrete, cement screeds and most waterproofing layers.
- Applicable even to irregular substrates.

Fields of application

ISOFLEX-PU 540 is suitable for waterproofing:

- Under tiles in wet areas (bathrooms and kitchens), balconies, auxiliary rooms, etc., as long as quartz sand has been previously broadcast on its last layer.
- Flat roofs and balconies.
- Under thermal insulation boards on flat roofs.
- Foundations.

When applied on exposed surfaces, the use of the protective topcoat TOPCOAT-PU 720 is required.

Technical characteristics

1. Liquid properties

Form:	polyurethane prepolymer
Colors:	black, grey
Density:	1.48 ± 0.02 kg/l
Viscosity:	3,500 ± 1,500 mPa·s (at +23°C)

2. Membrane properties

Elongation at break: (EN-ISO 527)	> 400%
Tensile strength: (EN-ISO 527)	> 3 N/mm ²
Hardness according to SHORE A:	78-83
Adhesion: (EN 1542)	> 2 N/mm ²
Service temperature:	from -30°C to +80°C

Directions of use

1. Substrate preparation

In general, the substrate must be dry (moisture content < 4%), clean, free of grease, loose particles, dust, etc.

1.1 Concrete substrates

Any existing cavities in concrete should be repaired in advance.

Severe cracks in the substrate must be primed locally and after 2-3 hours (depending on the weather conditions) must be sealed with the polyurethane sealants FLEX PU-30 S or FLEX PU-50 S.

Concrete and other porous surfaces with moisture content < 4% should be treated with the primer PRIMER-PU 100, with a consumption of approx. 200 g/m².

Substrates with moisture content > 4% should be primed with the special primer PRIMER-PU 140, with a consumption of 200-300 g/m².

1.2 Smooth and non-absorbent substrates

Smooth and non-absorbent surfaces, as well as surfaces with bituminous membranes or other old waterproofing layers, must be primed with the water-based epoxy primer EPOXYPRIMER 500, thinned with water up to 30% by weight. The product is applied by brush or roller in one coat.

Consumption: 150-200 g/m².

Depending on the weather conditions, ISOFLEX-PU 540 is applied within 24-48 hours from priming, as soon as moisture content falls below 4%.

2. Application – Consumption

Before application, it is recommended to slightly stir ISOFLEX-PU 540 until a homogeneous mixture is formed. Extensive stirring should be avoided in order to prevent air entrapment in the material.

a) Total waterproofing of the surface

ISOFLEX-PU 540 is applied by brush or roller in two layers. The first layer is applied 5-6 hours after priming and while PRIMER-PU 100 is still tacky. The second layer should be applied crosswise after 8-24 hours, depending on the weather conditions.

Consumption: approx. 1.2-1.5 kg/m², depending on the substrate.

ISOFLEX-PU 540

In case of dense, multiple cracks all over the surface, it is strongly recommended to fully reinforce ISOFLEX-PU 540 membrane with 100 cm wide strips of polyester fleece (60 g/m²). These placed strips must overlap by 5-10 cm. In that case, 5-6 hours after priming, the first layer of ISOFLEX-PU 540 is applied covering the reinforcement to a width of 100 cm, and, while still fresh, a strip of polyester fleece is embedded. The same application process is followed over the remaining surface.

Two extra layers of ISOFLEX-PU 540 are applied over the entire surface.

Consumption: approximately 2.20-2.50 kg/m², depending on the substrate.

b) Local waterproofing of cracks

In this case, the primer is applied on the substrate only across the cracks, to a width of 10-12 cm. Five-six hours after priming, the first ISOFLEX-PU 540 layer is applied and, while still fresh, a 10 cm wide polyester fleece strip (60 g/m²) is embedded lengthwise. Then, two extra ISOFLEX-PU 540 layers are applied along the cracks, completely covering the reinforcement.

Consumption: approximately 220-250 g/m of crack length.

c) Waterproofing under tiles

ISOFLEX-PU 540 is applied by brush or roller in two layers.

ISOFLEX-PU 540 should be locally reinforced along joints and wall-floor junctions by embedding a 10 cm wide polyester fleece strip on its first layer, while still fresh.

After the application of the final layer and while it is still fresh, quartz sand (Ø 0.3-0.8 mm) must be broadcast. The quartz sand must be completely dry.

Consumption of quartz sand: approx. 3 kg/m².

After 24 hours, any loose grains should be removed with a high suction vacuum cleaner. Tiles should be fixed with a high performance, polymer-modified tile adhesive, such as ISOMAT AK 22, ISOMAT AK 25, ISOMAT AK-ELASTIC and ISOMAT AK-MEGARAPID.

Tools should be cleaned with SM-16 solvent while ISOFLEX-PU 540 is still fresh.

Packaging

Metal containers of 6 kg and 25 kg.

Shelf life – Storage

9 months from production date if stored in original, unopened packaging at temperatures between +5°C and +35°C. Protect from direct sunlight and frost.

Remarks


- In case of application by spray, it may be diluted, depending on the weather conditions, up to 10%, only with the special solvent SM-16.
- ISOFLEX-PU 540 is not suitable for contact with chemically treated water of swimming pools.
- Temperature during the application and hardening of the product should be between +8°C and +35°C.
- The consumption of ISOFLEX-PU 540 should not exceed 750 g/m² per layer.
- Opened containers should be used at once and cannot be re-stored.
- ISOFLEX-PU 540 is intended for professional use only.

Volatile Organic Compounds (VOCs)

According to Directive 2004/42/CE (Annex II, table A), the maximum allowed VOC content for the product subcategory i, type SB is 500 g/l (2010) for the ready-to-use product.

The ready-to-use product ISOFLEX-PU 540 contains a maximum of 500 g/l VOC.

ISOFLEX-PU 540

 2032
ISOMAT S.A. 17 th km Thessaloniki – Ag. Athanasios P.O. BOX 1043, 570 03 Ag Athanasios, Greece 18
2032-CPR-10.11E DoP No.: ISOFLEX-PU 540 / 1869-01 EN 1504-2 Surface protection products Coating Permeability to CO ₂ : Sd > 50m Water vapor permeability: Class I (permeable) Capillary absorption: w < 0.1 kg/m ² ·h ^{0.5} Adhesion: ≥ 0.8 N/mm ² Reaction to fire: Euroclass F Dangerous substances comply with 5.3

ISOMAT S.A.
BUILDING CHEMICALS AND MORTARS
MAIN OFFICES - FACTORY:
17th km Thessaloniki - Ag. Athanasios Road,
P.O. BOX 1043, 570 03 Ag. Athanasios, Greece,
Tel.: +30 2310 576 000, Fax: +30 2310 722 475
www.isomat.eu e-mail: info@isomat.eu

The technical information and instructions supplied in this datasheet are based on the knowledge and experience of the Research and Development Department of our company and on results from long-term applications of the product in practice. The recommendations and suggestions referring to the use of the product are provided without guarantee, since site conditions during the applications are beyond the control of our company. Therefore the user is responsible for confirming that the chosen product is suitable for the envisaged application. The present edition of this technical datasheet automatically cancels any previous one concerning the same product.

